

BESCHEINIGUNG ♦ ATTESTATION ♦ 证明书 ♦ СВИДЕТЕЛЬСТВО ♦ CONSTANCIA ♦ ATTESTAZIONE



Annex No : 1

Certificate No : Z-IS-TGK-IST-25-07-5010011896-25-IS-0466a-34-T-01



Türkiye

PIPE CLAMP WITH NUT TENSILE TEST RESULTS

 Norm Bağlantı ve Tesbit Elemanları San. Tic. Ltd. Şti.				Test Date : 03.07.2025	
Product Code	Dimension	Tested Sample	Catalogue Fracture Value (kN)	Fracture Value (kN)	Fracture area / Type
NSC 006	1/8"	1	3,9 kN	6,048	Tear of Bolt
		2		4,404	Tear of Bolt
		3		6,173	Tear of Bolt
NSC 008	1/4"	1	3,9 kN	6,463	Tear of Bolt
		2		6,790	Nut snapped off
		3		6,367	Tear of Bolt
NSC 010	3/8"	1	3,9 kN	7,132	Sheet Metal
		2		5,833	Nut snapped off
		3		8,792	Tear of Bolt
NSC 015	1/2"	1	3,9 kN	6,324	Sheet Metal
		2		6,590	Tear of Bolt
		3		6,309	Bolt stripped
NSC 020	3/4"	1	3,9 kN	4,252	Tear of Bolt
		2		5,412	Tear of Bolt
		3		5,225	Nut snapped off
NSC 025	1"	1	3,9 kN	5,850	Tear of Bolt
		2		5,886	Nut snapped off
		3		6,283	Tear of Bolt
NSC 032	1 1/4"	1	4,8 kN	6,338	Tear of Bolt
		2		5,289	Tear of Bolt
		3		7,428	Tear of Bolt
NSC 040	1 1/2"	1	4,8 kN	5,376	Tear of Bolt
		2		5,143	Tear of Bolt
		3		6,121	Nut snapped off
NSC 050	2"	1	4,8 kN	6,228	Tear of Bolt
		2		5,413	Tear of Bolt
		3		6,171	Tear of Bolt
NSC 065	2 1/2"	1	6,9 kN	9,265	Sheet Metal
		2		10,544	Nut snapped off
		3		10,885	Sheet Metal
NSC 080	3"	1	6,9 kN	11,670	Sheet Metal
		2		9,714	Sheet Metal
		3		8,384	Bolt stripped
NSC 100	4"	1	6,9 kN	9,019	Sheet Metal
		2		10,536	Tear of Bolt
		3		10,472	Sheet Metal
NSC 125	5"	1	7,8 kN	12,812	Tear of Bolt
		2		12,287	Tear of Bolt
		3		11,273	Tear of Bolt
NSC 150	6"	1	7,8 kN	11,466	Tear of Bolt
		2		11,930	Sheet Metal
		3		12,365	Tear of Bolt
NSC 200	8"	1	7,8 kN	11,670	Tear of Bolt
		2		11,859	Tear of Bolt
		3		10,919	Tear of Bolt



TGK IS 306

Annex No : 1

Certificate No : Z-IS-TGK-IST-25-07-5010011896-25-IS-0466a-34-T-01
PIPE CLAMP WITH COMBI NUT TENSILE TEST RESULTS



 Norm Bağlantı ve Tesbit Elemanları San. Tic. Ltd. Şti.				Test Date :03.07.2025	
Product Code	Dimension	Tested Sample	Catalogue Fracture Value (kN)	Fracture Value (kN)	Fracture area / Type
NKSC 006	1/8"	1	3,9 kN	6,725	Sheet Metal
		2		4,732	Nut snapped off
		3		6,734	Tear of Bolt
NKSC 008	1/4"	1	3,9 kN	6,289	Tear of Bolt
		2		6,669	Tear of Bolt
		3		7,276	Bolt stripped
NKSC 010	3/8"	1	3,9 kN	5,622	Sheet Metal
		2		6,968	Tear of Bolt
		3		6,735	Sheet Metal
NKSC 015	1/2"	1	3,9 kN	6,695	Sheet Metal
		2		6,512	Sheet Metal
		3		6,846	Bolt stripped
NKSC 020	3/4"	1	3,9 kN	6,330	Tear of Bolt
		2		6,425	Tear of Bolt
		3		5,172	Bolt stripped
NKSC 025	1"	1	3,9 kN	6,482	Tear of Bolt
		2		4,946	Nut snapped off
		3		5,131	Tear of Bolt
NKSC 032	1 1/4"	1	4,8 kN	7,580	Tear of Bolt
		2		7,472	Tear of Bolt
		3		7,792	Bolt stripped
NKSC 040	1 1/2"	1	4,8 kN	7,644	Tear of Bolt
		2		7,032	Tear of Bolt
		3		7,476	Bolt stripped
NKSC 050	2"	1	4,8 kN	7,701	Tear of Bolt
		2		7,508	Tear of Bolt
		3		7,911	Tear of Bolt
NKSC 065	2 1/2"	1	6,9 kN	10,517	Sheet Metal
		2		11,189	Sheet Metal
		3		10,097	Sheet Metal
NKSC 080	3"	1	6,9 kN	11,453	Sheet Metal
		2		11,239	Sheet Metal
		3		9,035	Bolt stripped
NKSC 100	4"	1	6,9 kN	7,819	Sheet Metal
		2		11,264	Sheet Metal
		3		10,182	Sheet Metal
NKSC 125	5"	1	7,8 kN	12,679	Tear of Bolt
		2		11,889	Tear of Bolt
		3		11,908	Sheet Metal
NKSC 150	6"	1	7,8 kN	11,469	Tear of Bolt
		2		10,670	Sheet Metal
		3		11,425	Nut snapped off
NKSC 200	8"	1	7,8 kN	10,562	Tear of Bolt
		2		9,311	Tear of Bolt
		3		11,176	Tear of Bolt



TGK IS 306